












TRIPARK Technical Data Sheet

Type & Composition	Standard	SPC Vinyl Flooring Covering		
Application		Residential: Lifetime Comercial: 25 Years		
Surface Treatment		PPG lacquer (anti-bacterial & skid resistance)		
Profile		Painted bevel		
Plank Size	EN 427	60" x 7"		
Total Thickness (mm)	EN 428	6.0mm		
Wearlayer Thickness (mm)	EN 429	0.50mm (20mil)		
Fire Rating	EN 13501-1	Bf1-S1		
	Mekel Burner Test	Pass		
Heat Stability	KSM 3802	0.04% (80°C, 6hr)		
Slip Resistance	BS 7976-2	Pendulum Test: Low		
		Rz Surface Roughness: Moderate		
Residual Indentation	EN 433	≤0.1		
Color Fastness	ISO 105-B02	≥6		
Dimensional Stability	EN 434	≤0.25%		
Flexibility	EN 435	No Crack was found		
Electrial Behavior	EN 1081	Pass		
STC/IIC	72/76	Pass		
Characteristics	Standard			
	EN	Result	ASTM	Result
Size	EN 427	Pass	ASTM F536	Pass
Overall Thickness	EN 428	Pass	ASTM F386	Pass
Wearlayer Thickness	EN 429	Pass	ASTM F410	Pass
Dimension Squareness and Straightness	EN 427	Pass		
		Squareness: 0.16mm		
		Straightness: 0.06mm		
Chemical Resistance	EN 423	Pass	ASTM F 925	Pass
			ASTM F 1344	
Color Fastness to Artificial Light	EN 20105: B02 Method A	Pass, Grade ≥6	ASTM F 1515	Pass
Heat Stability to Color Change			ASTM F1514	Pass
Castor Chair Stability	EN425	Pass		
Residual Indentation	EN 433	Pass, 0.06 mm	ASTM F 1914	Pass
			ASTM F 970	
Abrasion Group	EN 660-1/2	Group T	ASTM F 510	Pass
			ASTM D 3384	
Impact Resistance			ASTM F 1265	Pass
			ASTM D 2632	
Dimensional Stability	EN 434	Pass	ASTM F 2199	Pass. 0.1%
Sound Reduction	EN ISO 717-2	2dB		
Flexibility	EN 435 Method A	Pass	ASTM F 137	Pass
Slip Resistance	EN 13893	Class DS	ASTM D 2047-93	Pass
Electrial Resistance	EN 1081 Method C	Pass	ASTM F 150-06	Pass
Thermal Resistance	EN 12664	Pass		
Toxic Element Test	EN 71-3	Pass, Not toxic, Does not contain heavy metal and formaldehyde		
Behaviour to Fire	EN ISO 11925-2	Bf1-S1	ASTM E 648-06	Pass/Class 1
	EN 13501-1			
	EN ISO 9239-1			
Smoke Density			ASTM E 662	Pass. <450
 CERTIFIED BY SCS Global Services	 100% WATERPROOF	 IXPE FOAM REDUCES BOTH REFLECTIVE NOISE AND THROUGH-THE-FLOOR SOUND		
	 100% VIRGIN MATERIAL FORMALDEHYDE FREE	 ANTIMICROBIAL UV COATING		
	 WEAR LAYER 20MIL	 AQI LESS THAN 50 EXCELLENT		
	 STAIN RESISTANT	 25 YEARS FOR COMMERCIAL		
	 ENHANCED DURABILITY & SKID RESISTANCE & WEAR-RESISTING	 LIFETIME FOR RESIDENTIAL		